

CDM 160 - Corroplast AB

Premix plaster

Reference No.	TDS / 100 / CPAB
Issue Date:	January 2020
Revision No.	4

Product Features

Corroplast AB is a cementitious dry mix plaster/render consisting of portland cement, graded aggregates, fibre & special chemical additives to obtain a homogeneous mix and get good shrinkage control and workability.

Corroplast AB is durable, has good adhesion and excellent mechanical properties.

Typical Uses

Corroplast AB is recommended for internal and external plastering of AAC blocks, Concrete blocks, ceilings and concrete surfaces. **Corroplast AB** can be applied traditionally by hand or by using modern plaster spraying machines. It should not be used on painted surfaces or floors.

Technical Data	
Appearance	: Grey colour powder form
Composition	: Portland cement, select crushed aggregates & specific additives
Grain size	: 0 to 1.7 mm
Water application	: 16 to 18 %
Wet density	: 1.6 ± 0.10 kg/l
Wet mix life	: < 2 hours @ 20°C
Wet Volume	: 635 l/ton
Working time	: approx 60 minutes
Compressive strength	: 4 N/mm ²
Flexural strength	: 1 N/mm ²
Applicable Standards	: ASTM C926, C897, BS EN 196, BS 5262, BS 5492, BS EN 998
Coverage per ton @ 15mm thickness *	: Approx. 42 m ²

Directions for Use

Preparation

Long term durability and function can only be achieved with good preparation to give a strong mechanical bond to the substrate and complete void filling.

All substrates must be clean, sound, dust free, and free from all traces of oil and chemicals.

The surface has to be dampened with potable water before application.

Corroplast AB is recommended to be applied directly on block works without using rush coat. However, **Corroplast Keycoat N** or **Corroplast Keycoat MS** are recommended to be applied on smooth concrete prior to the application of **Corroplast AB**.

Mixing

Mix manually or mechanically a 40 kg bag of **Corroplast AB** with 6.5 - 7 litres of potable water until homogeneous paste is obtained. Leave the mix a few minutes.

If a spraying machine is used, mixing is carried out automatically.

Application

The plaster is now ready for application by machine or manually with a plastering trowel. Apply the plaster on the prepared surface at a thickness between 10 and 20 mm in one layer.

If more thickness is required, the application should be done in 2 layers. Leave the first layer rough, allow to cure and apply the second layer within 48 hours after the first one.

Finish the surface with a soft synthetic sponge or wooden/plastic float.

Let the product set properly on the surface before any curing.

Curing

Protect the **Corroplast AB** from direct sunshine and wind.

The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

Cleaning

Clean tools and equipment immediately after use with detergent and water.

ESTIMATION

Corroplast AB is available in 40 kg bag. Coverage rate approximately 1.58 kg per m² @ 1 mm thickness.

Note: All coverage rates given are theoretical and subject to actual site conditions, wastage factors & the method/skill of applicators. We recommend trial areas are done to establish practical consumption.

Limitations

Substrate temperatures should be above 5°C and rising.

Avoid application if the work area may be subject to the onset of rain or moving water.

CDM 160 - Corroplast AB

Premix Plaster

Do not part mix under any circumstances.

All products should be used within the pot life. Materials not used within the specified time should be discarded.

If the above general application details do not meet with your requirements, please contact CCCDrymix for a project specific method statement.

Health & Safety

Always use appropriate PPE including gloves, goggles and a barrier cream to avoid contact with skin and eyes.

Should contact with skin or eyes occur, wash immediately with plenty of clean water and seek medical advice.

If swallowed, seek medical attention immediately. Do not induce vomiting.

Avoid inhalation and ensure adequate ventilation or suitable respiratory equipment if working in confined spaces.

Do not expose products to fire or naked flames under any circumstances.

Always refer to the product Material Safety Data Sheet (MSDS) for full health & safety and handling recommendations.

Storage

Corroplast AB has a maximum shelf life of 12 months from the date of manufacture.

To maximize shelf life always store products in their original, unopened packaging in a dry environment, away from direct sunlight with a minimum temperature of 10°C but not exceeding 45°C.

Damaged packaging, high humidity or extreme temperatures may reduce the shelf life.

Warranty

The raw materials used in the manufacture are of high quality. However, weather and ambient temperatures, amount of water added, preparation and conditions of base coat, as well as care exercised in application, are factors over which we have no control. We assume no warranty for finished work, either expressed or implied.