

CDM 165 - Corroplast Thin Coat

Reference No.	TDS / 100 / CPTC
Issue Date:	November 2016
Revision No.	1

Thin coat finishing plaster on concrete or AAC blocks

Product Features

Corroplast Thin Coat is a cementitious premix plaster used to carry out plastering works in thin layer up to a thickness of 4 - 6 mm. Due to its high content in additives it has better shrinkage control and workability.

Corroplast Thin Coat can be used directly on blocks. It is durable and has good adhesion.

Typical Uses

Corroplast Thin Coat is recommended for internal plastering on Concrete/AAC blocks, ceilings and concrete surfaces. It can be applied by hand or by using plaster-spraying machines. It should not be used on painted surfaces or floors.

Technical Data	
Appearance	: Grey color powder form
Composition	: Portland cement, select crushed aggregates and specific additives
Grain size	: 0 to 0.8 mm
Water ratio	: 20 to 22 %
Wet density	: 1.7 ± 0.10 kg/l
Wet mix life	: < 2 hours @ 20°C
Wet Volume	: 600 l/ton
Working time	: approx 60 minutes
Compressive strength	: 5 N/mm ²
Flexural strength	: 1 N/mm ²
Applicable Standards	: ASTM C926, C897, BS EN 196, BS5262, BS5492
Consumption	: Approximately 1.7 kg per m ² at 1 mm thickness

Directions for Use

Preparation

Long term durability and function can only be achieved with good preparation to give a strong mechanical bond to the substrate and complete void filling.

All substrates must be clean, sound, dust free, and free from all traces of oil and chemicals.

The surface has to be dampened with potable water before application.

Corroplast Thin Coat is recommended to be applied directly on block works without using rush coat. However, **Corroplast Keycoat N** or **Corroplast Keycoat MS** are recommended to be applied on smooth concrete prior to the application of **Corroplast Thin Coat**.

Mixing

Mix manually or mechanically a 40 kg bag of **Corroplast Thin Coat** with 8 - 9 litres of potable water until homogeneous paste is obtained. Leave the mix a few minutes.

If a spraying machine is used, mixing is carried out automatically.

Application

The plaster is now ready for application by machine or manually with a plastering trowel. Apply the plaster on the prepared surface at a thickness between 4 and 6 mm in one layer.

Finish the surface with a soft synthetic sponge or wooden/plastic float.

Let the product set properly on the surface before any curing.

Curing

Protect the **Corroplast Thin Coat** from direct sunshine and wind.

The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

Cleaning

Clean tools and equipment immediately after use with detergent and water.

Estimating

All coverage rates given are theoretical and subject to actual site conditions. We recommend trial areas are done to establish practical consumption.

Corroplast Thin Coat is available in 40 kg bag. Coverage rate approximately 1.7 kg per m² @ 1 mm thickness.

Limitations

Substrate temperatures should be above 5°C and rising.

Avoid application if the work area may be subject to the onset of rain or moving water.

Do not part mix under any circumstances.

CDM 165 - Corroplast Thin Coat

Thin coat finishing plaster on concrete and AAC blocks

All products should be used within the pot life. Materials not used within the specified time should be discarded.

If the above general application details do not meet with your requirements, please contact CCCDrymix for a project specific method statement.

Health & Safety

Always use appropriate PPE including gloves, goggles and a barrier cream to avoid contact with skin and eyes.

Should contact with skin or eyes occur, wash immediately with plenty of clean water and seek medical advice.

If swallowed, seek medical attention immediately. Do not induce vomiting.

Avoid inhalation and ensure adequate ventilation or suitable respiratory equipment if working in confined spaces.

Do not expose products to fire or naked flames under any circumstances.

Always refer to the product Material Safety Data Sheet (MSDS) for full health & safety and handling recommendations.

Storage

Corroplast Thin Coat has a maximum shelf life of 12 months from the date of manufacture.

To maximize shelf life always store products in their original, unopened packaging in a dry environment, away from direct sunlight with a minimum temperature of 10°C but not exceeding 45°C.

Damaged packaging, high humidity or extreme temperatures may reduce the shelf life.

Warranty

The raw materials used in manufacturing are of high quality. However, weather and ambient temperatures, amount of water added, preparation and conditions of base coat, as well as care exercised in application, are factors over which we have no control. We assume no warranty for finished work, either expressed or implied.