

CDM 450 - Corrodeco GP

One coat decorating render

Reference No.	TDS / 400 / CDGP
Issue Date:	January 2020
Revision No.	2

Product Features

Corrodeco GP is a one coat decorating render consisting of UV resistant color pigments, graded aggregates, cement and additives to carry out rendering works.

Corrodeco GP is available in variety of colors. Different textures like fine, wavy, heritage and other finishes can be attained.

Typical Uses

Corrodeco GP can be applied on various substrates, including old substrates, shuttered concrete walls, over concrete or masonry blocks and various approved renderings.

Technical Data	
Appearance	: White cement base with pigments
Composition	: Cement, special sands, mineral pigments and special additives
Grain size	: 0 to 1.5 mm
Water application	: 17%
Wet density	: 1.7 ± 0.10 kg per litre
Wet Volume	: 600 l/ton
Wet mix life	: < 2 hours @ 20°C
Working time	: approx 60 minutes
Compressive strength	: 8.5 N/mm ²
Flexural strength	: 2 N/mm ²
Applicable Standards	: ASTM C926, C897, BS EN 196, BS 5262, BS5492
Coverage per ton @ 15mm thickness *	: Approx. 40 m ²

Directions for Use

Preparation

The substrate must be clean, sound, dust free and without any traces of plaster or paint.

Planimetry and plumbline must be compliant with building regulations in force.

Corrodeco GP is recommended to be applied directly on block works without using a key coat. However, **Corroplast Keycoat N** or **Corroplast Keycoat MS** are recommended to be applied on smooth concrete prior to the application of **Corrodeco GP**.

Mixing

Machine-mix one 35 kg bag of **Corrodeco GP** with 6 litres of clean water for approximately 5 minutes until a homogeneous mix is achieved.

If a spray plastering machine is used mixing is carried out automatically. Maintain the consistent water dosage throughout to avoid colour variations.

Application

The plaster is now ready for application by machine or manually with a plastering trowel. Apply the plaster on the prepared surface at a thickness between 10 and 20 mm in one layer.

If more thickness is required, the application should be done in 2 layers. Leave the first layer rough, allow to cure and apply the second layer within 48 hours after the first one.

Finish with a wooden, plastic or sponge-backed float as desired for scraped, floated, Rustic, wavy and trowelled finishes

Note on thickness: Appropriate thickness must be maintained, as needed to obtain above finishes.

Curing

Protect the new surface applied from sunshine and wind.

The new plaster/render has to be cured with water for at least three days by spraying 3 to 4 times daily.

Cleaning

Clean tools & equipment immediately after use with detergent and water.

CDM 450 - Corrodeco GP

One coat decorating mortar

Estimating*

All coverage rates given are theoretical and subject to actual site conditions. We recommend trial areas are done to establish practical consumption.

Corrodeco GP is available in 35 kg bag. Coverage rate approximately 1.7 kg per m² @ 1 mm thickness.

Limitations

Application temperature range should be between +5°C to +45°C.

For professional use only.

Dampen the substrate prior to application, dampen the mortar after application.

Health & Safety

Always use appropriate PPE including gloves, goggles and a barrier cream to avoid contact with skin and eyes.

Should contact with skin or eyes occur, wash immediately with plenty of clean water and seek medical advice.

If swallowed, seek medical attention immediately. Do not induce vomiting.

Avoid inhalation and ensure adequate ventilation or suitable respiratory equipment if working in confined spaces.

Do not expose products to fire or naked flames under any circumstances.

Always refer to the product Material Safety Data Sheet (MSDS) for full health & safety and handling recommendations.

Storage

Corrodeco GP has a maximum shelf life of 12 months from the date of manufacture.

To maximize shelf life always store products in their original, unopened packaging in a dry environment, away from direct sunlight with a minimum temperature of 10°C but not exceeding 45°C.

Damaged packaging, high humidity or extreme temperatures may reduce the shelf life.

Warranty

The raw materials used in the manufacture are of high quality. However, weather and ambient temperatures, amount of water added, preparation and conditions of base coat, as well as care exercised in application, are factors over which we have no control. We assume no warranty for finished work, either expressed or implied.