

CDM 450 - Corrodeco GP

One coat decorating mortar

Reference No.	TDS / 400 / CDGP
Issue Date:	May 2015
Revision No.	1

Product Features

Corrodeco GP is a one coat color decorating mortar for vertical masonry and concrete walls.

Corrodeco GP is applied in 10 to 20 mm thickness, as its fine finish can be scraped, floated or rustic. The product is highly durable, maintenance free and UV resistant.

Typical Uses

Corrodeco GP can be applied on various substrates, including old substrates, shuttered concrete walls, over concrete or masonry blocks and various approved renderings.

Technical Data	
Appearance	: White cement base with pigments
Composition	: Cement, special sands, mineral pigments and special additives
Grain size	: 0 to 1.5 mm
Water application	: 17%
Wet density	: 1.8 ± 0.10 kg per litre
Wet Volume	: 650 l/ton
Wet mix life	: < 2 hours @ 20°C
Working time	: approx 60 minutes
Compressive strength	: 4 N/mm ²
Flexural strength	: 1 N/mm ²
Applicable Standards	: ASTM C926, C897, BS EN 196, BS 5262, BS5492
Consumption	: 1.8 kg per m ² at 1 mm thickness

Directions for Use

Preparation

The substrate must be clean, sound, dust free and without any traces of plaster or paint.

Planimetry and plumbline must be compliant with building regulations in force.

Corrodeco GP is recommended to be applied directly on block works without using a key coat. However, **Corroplast Keycoat N** or **Corroplast Keycoat MS** are recommended to be applied on smooth concrete prior to the application of **Corrodeco GP**.

Mixing

Machine-mix one 35 kg bag of **Corrodeco GP** with 6 litres of clean water for approximately 5 minutes until a homogeneous mix is achieved.

If a spray plastering machine is used mixing is carried out automatically. Maintain the consistent water dosage throughout to avoid colour variations.

Application

For color rendering of concrete and masonry substrates:

For a rustic / knockdown rustic finish:

- Apply a level, compact 10 mm thick first coat.
- Allow to dry and then spray on the decorative coat at a thickness of 5 - 10 mm. The knockdown appearance is obtained by pressing a plastic or stainless steel float onto the stiffened coat.

For a scraped finish:

- Spray a level, compact 15 mm thick coat. Allow to dry (30 – 45 minutes) and then scrape.

For a floated finish:

- Apply a level, compact 7 - 8 mm thick first coat.
- Allow to harden and then apply a second coat.
- Finish with a wooden, plastic or sponge-backed float as desired.

Note on thickness: The overall covering thickness must be at least 10 mm before commencing with the rustic / knockdown rustic finishing and after executing the scraped or float finish.

For decorating concrete and masonry substrates (precoated with plaster such as Corroplast GP, Corroplast AB):

For a rustic / knockdown rustic finish:

- Apply a level, compact 5 mm thick first coat.
- Allow to dry and then spray on the decorative coat. The knockdown appearance is obtained by pressing a plastic or stainless steel float onto the stiffened coat.

For a scraped finish:

- Spray a level, compact 10 mm thick coat. Allow to dry (30 – 45 minutes) and then scrape.

Note on thickness: The overall covering thickness must be at least 5 mm before commencing with the rustic / knockdown rustic finishing and after executing the scraped finish.

Curing

Protect the new surface applied from sunshine and wind.

The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

Cleaning

Clean tools & equipment immediately after use with detergent and water.

CDM 450 - Corrodeco GP

One coat decorating mortar

Estimating

All coverage rates given are theoretical and subject to actual site conditions. We recommend trial areas are done to establish practical consumption.

Corrodeco GP is available in 35 kg bag. Coverage rate approximately 1.8 kg per m² @ 1 mm thickness.

Limitations

Application temperature range should be between +5°C to +45°C.

For professional use only.

Dampen the substrate prior to application, dampen the mortar after application.

Health & Safety

Always use appropriate PPE including gloves, goggles and a barrier cream to avoid contact with skin and eyes.

Should contact with skin or eyes occur, wash immediately with plenty of clean water and seek medical advice.

If swallowed, seek medical attention immediately. Do not induce vomiting.

Avoid inhalation and ensure adequate ventilation or suitable respiratory equipment if working in confined spaces.

Do not expose products to fire or naked flames under any circumstances.

Always refer to the product Material Safety Data Sheet (MSDS) for full health & safety and handling recommendations.

Storage

Corrodeco GP has a maximum shelf life of 12 months from the date of manufacture.

To maximize shelf life always store products in their original, unopened packaging in a dry environment, away from direct sunlight with a minimum temperature of 10°C but not exceeding 45°C.

Damaged packaging, high humidity or extreme temperatures may reduce the shelf life.

Warranty

The raw materials used in the manufacture are of high quality. However, weather and ambient temperatures, amount of water added, preparation and conditions of base coat, as well as care exercised in application, are factors over which we have no control. We assume no warranty for finished work, either expressed or implied.