

Corromix PC 800

High performance polycarboxylate based concrete admixture.

Reference No.	TDS / ADMIX / PC800
Issue Date:	August 2017
Revision No.	1

Product Features

Corromix PC 800 is a new generation superplasticizer based on modified polycarboxylate and synthetic polymers.

Thanks to its specifically designed molecular structure, **Corromix PC 800** enables the concrete manufacturer to produce cohesive, low viscous concrete with long workability retention.

Corromix PC 800 has been developed to maintain fresh concrete workability without compromising the setting time.

Corromix PC 800 enables the production of self-leveling concrete.

Benefits

- **Corromix PC 800** allows concrete with the importance on workability to be obtained, while reducing the water / cement ratio.
- Enhances the workability retention of concrete in hot climates.
- The dispersion properties of **Corromix PC 800** allow the user to optimise the cement content when a specified mechanical strength is required.

Areas of application

Corromix PC 800 is recommended for all concrete mixes where water content, improved cementitious material performance, high workability retention and very high strengths characteristics are desirable.

1. All types of cement
2. Heavy prefabrication
3. High performance concrete, ultra high performance concrete
4. Pre-stressed concrete
5. Ready-mix concrete
6. Concrete of humid, plastic or fluid consistency
7. Normal or high flowable concrete
8. High strength concrete with high workability retention
9. Compatible with Micro silica, GGBS and Fly Ash.
10. Extended workability concrete
11. White or pale concrete

Description

Corromix PC 800 is a chemically stable liquid.

1. Nature : liquid
2. Colour : Brownish
3. Density : 1.05 ± 0.020
4. pH : 5 ± 2

Corromix PC 800 does not contain any added calcium

chloride or other chloride based components. It will not promote or contribute to corrosion of reinforcing steel in concrete.

Packaging

- Bulk
- IBC: 1000 L

Standard specifications

Corromix PC 800 conforms to ASTM C 494 Type A, F and G.

Directions for use

Dosage

Between 0.5 and 2.5 kg per 100 kg of total cementitious material. A 1.0 % dosage of the product to the weight of cement is commonly used.

Corromix PC 800 can be added to the water before mixing the concrete, however, if needed it can be added to the concrete after mixing.

Dosage rates of **Corromix PC 800** are dependent upon desired concrete performance characteristics and variables including cement quantity and chemistry, concrete temperature and curing conditions.

Because local climate conditions vary, please contact your local Corrotech sales representative for further assistance if using outside recommended dosage ranges.

Compatibility

Corromix PC 800 is compatible with all types of Portland cement, class C and F fly ash, slag, microsilica, fibers and approved air entraining admixtures.

Precaution

- Protect from frost. Use **Corromix PC 800** at a temperature above to 10°C.
- Do not allow product to freeze
- This product must be stored in plastic containers. Avoid the use of PVC containers.
- Shelf life: 12 months.

Safety

Corromix PC 800 is not considered dangerous to handle. Please refer to the material safety data sheet for additional information.