

METZ 6NF

CHEMICAL GRADE EPOXY NOVOLAC



DESCRIPTION:

Metz 6NF is a 100% solids Epoxy Novolac formulation which imparts outstanding chemical resistance. It is specifically formulated to resist concentrated acid environments, including sulphuric, hydrochloric and phosphoric acids. It also cures rapidly even at low temperatures, thus minimising downtime. Metz 6NF is used to bed and joint acid resistant bricks and tiles.

FEATURES AND BENEFITS:

- **Outstanding Chemical Resistance**
Resistant to a wide range of concentrated acids and alkalis, solvents, oils and fats. Resistant to spillages of concentrated sulphuric, hydrochloric, and phosphoric acids. Refer Metz Chemical Resistance Chart for full details.
- **High Temperature Resistance**
Resistant to temperatures up to 150°C.
- **High Bond, Tensile and Compressive Strengths**
- **Solventless**
100% solids formulation.
- **Rapid Cure**
Fast setting, minimises downtime.
- **Low Temperature Cure**
Cures at temperatures down to 0°C.

RECOMMENDED:

As a bedding and jointing material for acid brick and tile installations in:

- Secondary containment linings.
- Acid plants.
- Fertiliser plants.
- Oil refineries.
- C.I.P. rooms in food and beverage plants.

NOT RECOMMENDED:

- For exposure to strong organic acids and solvents. Refer Metz 12P and Metz 7K

Note: Metz 6NF may change colour on exposure to concentrated acids.

PHYSICAL PROPERTIES:

| | (Typical Values) |
|------------------------------------|------------------|
| Density, g/cm ³ : | 1.9 - 2.0 |
| Compressive Strength, MPa: | 100 |
| Adhesion to Brick, MPa: | 2.8 |
| Maximum Service Temperature, deg C | 150 |
| Tensile Strength, MPa: | 21 |

COVERAGE:

 Theoretical quantities (allow for wastage)

For jointing 240 x 115mm tiles - joints 6mm wide x 20mm deep

3 kg/square metre

For jointing 150 x 150mm tiles - joints 6mm wide x 12mm deep

1.85 kg/square metre

For bedding tiles

2 kg/square metre/mm of thickness



METZ 6NF

CHEMICAL GRADE EPOXY NOVOLAC



INSTRUCTIONS FOR USE

1. Temperature of Working Area

For optimum results, maintain a temperature of 5 - 40°C on air, substrate and components during mixing, application and curing.

At temperatures below 5°C, the application becomes more difficult and curing is retarded.

At temperatures above 40°C, initial set will take place rapidly. This difficulty can be overcome by mixing in a cooler area or by cooling the components.

Note: Materials should be kept as cool as possible. Reducing material temperature will increase pot life.

2. Surface Preparation

All surfaces must be clean, dry and free from oil, grease, water and other contaminants which may inhibit bond.

3. Mixing

a) Mixing Equipment

Mechanical mixing is recommended. A low speed mixer or a heavy duty drill with an appropriate mixing paddle are suitable.

b) Mixing Proportions

| | By Weight | By Volume |
|----------------|-----------|------------|
| Liquid L2 | 2 | 1.85 parts |
| Hardener | 1 | 1.0 parts |
| Powder* P2, P1 | 9,10 | 7, 8 parts |

* For grouting tiles use P1 Powder, for bedding tiles use P2 Powder.

Note: Liquid to hardener ratio must not be altered under any circumstances. The powder proportion may be altered $\pm 10\%$ to suit requirements.

c) Mixing Procedure

Thoroughly mix liquid and hardener together first, in correct proportions. Add powder gradually with constant stirring.

d) Pot Life at 20°C - 40 minutes

30°C - 30 minutes

40°C - 20 minutes

e) Clean Up

Mixing equipment, tools, etc., can be cleaned with Metz Cleaner, xylene, acetone or M.E.K. prior to initial set of cement.

4. Installation

(a) Bedding

Use Metz P2 powder. For tiles, apply fresh mixed Metz 6NF to substrate with suitable notched trowel and immediately set tiles in the bed. When fixing tiles with keyed backs, prefill keys with Metz 6NF.

Do not spread more Metz 6NF that can be covered in 20 minutes at 20°C. When bedding bricks, bricks should be buttered with Metz 6NF using a trowel and well beaten down and tight against adjoining brick. Ensure there are no voids.

(b) Jointing

Use Metz P1 powder. Joint width: 6mm nominal to enable joints to be completely filled. Apply mixed grout to joints using trowel or compressed air operated jointing gun (operating at 100psi pressure). Ensure joints are flush with the tile surface.

Remove cement from the tile surface prior to the initial set of the cement, using Metz Cleaner or similar.

(c) Setting Time

at 20°C 6 hours

at 30°C 4 hours

at 40°C 3 hours

(d) Full Cure

at 20°C 3 days

at 30°C 2 days

at 40°C 2 days

Do not allow water or chemicals on the material surface for a minimum of 24 hours. For harsh chemical or physical environments, allow full cure prior to exposure.

5. Storage

Store in original, sealed container in a cool dry place. Under these conditions minimum shelf life is 12 months.

6. Safety Precautions

a) Liquid and Hardener:

Avoid contact with skin and eyes. Avoid breathing vapour.

Use barrier cream and wear protective gloves.

If contamination occurs, wash affected area with soap and water (never use Metz Cleaner for this purpose).

b) Powder:

Avoid breathing dust.

Ensure adequate ventilation.

c) Cleaner:

Inflammable.

No smoking.

Avoid formation of sparks.

Ensure adequate ventilation.

For full safety precautions refer to the Material Safety Data Sheet for each component.

Always ensure you have the latest data sheet version, refer www.metz.net.au

- The customer must comply strictly with the instructions contained in this product data sheet. Metz is not responsible for any advice or variations to this data sheet which are not confirmed in writing.
- If the customer has a claim against Metz in respect of any product supplied to the customer by Metz whether due to a fault in the product or the negligence or breach of contract by Metz or for any other reason:
 - Metz shall not be liable for any loss or damage including consequential loss or damage or loss of profits arising thereby;
 - Metz may at its option replace the defective product free of charge to the customer or refund all payments made to it by the buyer in respect of the defective product; and the maximum liability of Metz shall be the cost of replacing the defective product.

REV 09/12

**METZ SPECIALTY
MATERIALS PTY LTD**

A.C.N. 140 636 639

15A Stanton Road, Seven Hills, NSW 2147
Facsimile: (02) 9671 4292 Phone: (02) 9671 1311

6 University Place, Clayton North, VIC 3168
Facsimile: (03) 9561 6944 Phone: (03) 9561 6144

Unit 16, 42 Smith Street, Capalaba QLD 4157
Facsimile: (07) 3823 5552 Phone: (07) 3823 5555

Distributor